TDS 120-MATE TK-200 May-23





# **MATE TK-200**

## **SALES FORMAT**

15L, 4L





# **DESCRIPTION**

Matt plastic paint based on acrylic copolymers, deep matt finish. Improved formulation, minimises spattering caused by roller painting. Excellent balance between application, coverage, performance and washability. Suitable for professional use. Low VOC's and ammonia free. This product contributes to LEED, BREEAM and GREEN certifications.

ACCIDICATION ACCORDING TO LINE DI 42200

# **SCOPE OF APPLICATION**

Indoor/Outdoor. Decorative smooth coating, suitable for plaster mortars, plasterboard, concrete, fibre cement and other construction materials. Both new construction and maintenance. It has a pleasant scent that allows the painted space to be quickly inhabited. Suitable for painting premises in the health, catering, teaching, industrial and commercial sectors.

## **PROPERTIES**

- •Deep matt finish
- •Excellent coverage
- Good washability
- ·High performance
- •Pleasant aroma
- •Does not spread the flame

**Contains preservative ANTIMOLD** 

## **TECHNICAL DATA**

# Disponible TKROMATIC

Finishing	Deep matt			UNE EN 13300		
Brightness 85°.	 < 5			ISO 2813		
Particle size	Fino			ISO 1524		
Wet scrub resistance	Class 3 (31 microns)			ISO 11998		
Contrast Ratio / Opacity and Rendering	Class 1 (99.5%) for a theoretical yield of 5.0 m2/L and 90 microns of dry film Class 2 (98%) for a theoretical yield of 9.2 m2/L and 49.7 microns of dry film			ISO 6504-3		
Chemical composition	Aqueous dispersion of acrylic copolymers, pigments and extenders					
Colour	White and colours					
Berger Whiteness	86 ± 2			UNE 48073		
Theoretical performance	12-14 m2/L (40 microns dry)		ISO 23811			
Density	1,64 ± 0,05 g/ml		ISO 2811-1			
Viscosity	23 ± 3 Pa-s (20 rpm, R6)		ASTM D 2196-10			
Solids by volume	46 ± 2%		ISO 23811			
Levelling index	4 (+ 20% water)		UNE 48043			
Drop resistance	300 ± 25 microns (+ 20% water)		ISO 16862			
Fire classification	B-s1, d0			UNE-EN 13501-1	UNE-EN 13501-1	
VOC test	9.15 g/L		ISO 11890-2	NO. 095320-2		
VOC	< 10 g/l. EU maximum permitted value: 30 g/L.			2004/42/II A classification (a)		
Diluent	Mains water					
Dilution	0 to 20% depending on application system					
Repainting time	4-6 hours					
Drying time	Touch-drying 15-30 min		UNE 48301			
	Total Drying Washing:	30 min -1h 25-30 days				
Cleaning	Water					

# PREPARATION OF THE SUBSTRATE

#### **GENERAL**

The surface must be compact, dry, free of dust, salts, loose or poorly adhered parts or any type of contamination that may affect the adhesion of the system. The resistance of the substrate must be checked. Regardless of the substrate to be painted, the appearance must be homogenised and any differences in texture, gloss, absorption, etc. must be corrected.

#### **NEW WORK**

Type of substrate: plaster mortar, plasterboard, concrete, fibre cement and other building materials. Substrates in normal conditions: it is not necessary to apply a primer coat beforehand. Very porous and/or absorbent substrates: apply a coat of primer TKROM FIJATIVO F4, TKROM FIJATIVO AL AGUA PLIOTEC or TKROM FIJATIVO F10 BLANCO, in order to avoid excessive absorption in subsequent painting. Smooth surfaces with low absorbent power: apply a primer coat of TKROM FIJATIVO F1. In cases where the absorbent power of the substrate is very low, it is recommended to sand the surface to open the pores.

#### **RESTORATION AND MAINTENANCE**

Painted surfaces: materials in poor condition must be completely removed and the areas repaired until a sound, dry and clean substrate is obtained. Aged paintwork: it is advisable to apply a primer coat of TKROM FIJATIVO F1, in order to strengthen the outer layer by creating a resin grid that also allows transpiration, reduces absorption and facilitates subsequent painting. Aged, unpainted surfaces: the resistance of the substrate must be checked. For powdery, sandy and/or very absorbent surfaces, apply a coat of primer TKROM FIJATIVO F4, TKROM FIJATIVO AL AGUA PLIOTEC or TKROM FIJATIVO F10 BLANCO in order to regularise and fix the substrate. Substrates with microorganisms: remove mould and/or fungus by wet cleaning, apply one to two coats of TKROM LIMPIADOR REFORZANTE, leaving 12 hours between coats. If the substrate is very damaged, it is advisable to apply a coat of primer TKROM IMPRIMACIÓN SELLADORA-SANEADORA, following the manufacturer's instructions. Surfaces with efflorescence: remove efflorescence and alkalinity by means of suitable treatments, apply a coat of TKROM FIJATIVO F1 primer.

### **APPLICATION SYSTEM**

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
<b>PRIMING</b> (very porous substrates, unpainted aged surfaces, substrates with efflorescence)	TKROM FIJATIVO F4	14-18 m2/L layer	1:4 water	1 o 2
	TKROM FIJATIVO F10 BLANCO	14-18 m2/L layer	No dilution	1 o 2
	TKROM FIJADOR AL AGUA PLIOTEC	10-14 m2/L layer	No dilution	1 o 2
<b>PRIMING</b> (Surfaces with low absorbency, aged paints)	TKROM FIJATIVO PENETRANTE F1	14-18 m2/L layer	1:1 water	1 0 2
<b>PRIMING</b> (Carriers with micro-organisms)	TKROM LIMPIADOR REFORZANTE	N.A	No dilution	1 o 2
	TKROM IMPRIMACIÓN SELLADORA- SANEADORA	14-18 m2/L layer	No dilution	1 o 2
FINISH	TKROM MATE TK- 200	12-14 m2/L layer	0-20% Depending on application system	1 o 2



TDS 120-MATE TK-200 May-23

#### **CONDITIONS OF APPLICATION**

Min. +5°C / Max. +35°C Substrate Temp.

5°C / 35°C **Ambient Temperature** 

Cont. Humidity Substrate Dry substrate with humidity < 5%. Cement mortars, allow to set completely (28 days

minimum). Cementitious based products, allow to dry for at least 4 days before coating.

**Dew Point** The substrate temperature must be at least 3°C above the dew point to reduce the risk

of detachment or efflorescence.

## RECOMMENDATIONS FOR IMPLEMENTATION

Method of application Brush, roller and spray.

**Preparation** Shake to homogenise the product. Adjust viscosity with water. It is advisable to apply the

second coat of the product perpendicular to the first coat to achieve optimum opacity.

Maintenance It is not recommended to wash surfaces within 28 days of application.

#### RECOMMENDATIONS FOR IMPLEMENTATION

Health and safety

For any information concerning safety issues in the use, storage, transport and disposal of this product, users should consult the labelling and the most recent version of the product's MSDS, which contains the safety, ecological and toxicological information on the product.

LER CODE: 08 01 12. WASTE: NON-HAZARDOUS

**Storage** The stability of the product in its original unopened containers, at ambient temperatures

of not more than 30°C and not less than 5°C, shall be 24 months from the date of manufacture. Storage shall be in a cool, dry place, in their original containers, well closed,

undamaged and protected from frost and direct sunlight.

Tariff heading TARIC code: 3209 10 00

Note The technical information given in this document, as well as the recommendations

concerning the application and use of the product, are given in good faith, with data based on current knowledge of the product, laboratory tests and practical use under normal conditions of storage, handling and application. Complete reproducibility of the stated data for each individual use is not guaranteed. The user of the product should test

the suitability of the product in accordance with the end use of the product.



**EUPINCA, S.A** C/Londres, 13 Pol. Industrial Cabezo Beaza 30353 Cartagena, Murcia. T: +34 968 089 000 info@grupotkrom.com





