



# SUPERCARRARA RUGOSO

## SALES FORMAT

15L, 4L



## DESCRIPTION

A recently developed, rough-textured stone-effect revestimiento petreo for façades, based on high-tech vinyl copolymers. Waterproof and breathable, with excellent hardness, adhesion and resistance to atmospheric agents. Very good resistance to alkalinity and to severe environmental and industrial conditions.

## SCOPE OF APPLICATION

Outdoors. Preventative protection for new reinforced concrete structures in aggressive environments. A protective coating with a textured finish, suitable for both new and repaired substrates. Cement and lime mortars, concrete, aerated concrete. Fibre cement.

## PROPERTIES

- Highly resistant to alkalinity
- Highly resistant to atmospheric agents
- Lightfast solid colours
- Excellent water vapour permeability
- Waterproof against rainwater
- Resistant to cracking and yellowing
- High elasticity under structural movement
- Excellent adhesion
- Easy to apply

Contains an **ANTIMOLD** and **anti-algae preservative**

Disponible **TKROMATIC**

## TECHNICAL DATA

### CLASSIFICATION IN ACCORDANCE WITH UNE-EN-1062

#### CLASSIFICATION IN ACCORDANCE WITH UNE-EN-1062

Finish	G3 MATTE	UNE-EN 1062-1
Gloss 85°	< 5	ISO 2813
Dry film thickness	E3 (100–200 microns per coat)	UNE-EN 1062-1
Maximum particle size	S2 (<300 microns) Medium	UNE-EN 1062-1

#### ADDITIONAL TECHNICAL DATA

Chemical composition	Aqueous dispersion of vinyl copolymers	
Colour	White and colours	
Theoretical coverage	3–5 m <sup>2</sup> /L (150 dry microns)	ISO 23811
Density	1.55 ± 0.15 g/mL	ISO 2811-1
Viscosity	72 ± 15 Pa·s (20 rpm, R7)	ASTM D 2196-10
Volume solids	62 ± 5%	ISO 23811
VOC	<16 g/L. Maximum permitted by the EU: 40 g/L	2004/42/II A Classification (c)
Diluents	Tap water	
Dilution	0–20%, depending on the application method	
Recoating time	4–6 hours	
Drying time	Touch-dry: 30 mins   Fully dry: 20–30 days   Washable: 25–30 days	UNE 48301
Cleaning	Water	

The technical data specified may vary if the material is tinted.

## SUBSTRATE PREPARATION

---

### GENERAL RECOMMENDATIONS

Outdoors, do not apply if rain is forecast, in the midday sun or on damp days.

### UNPAINTED OR NEW SURFACES:

Outdoors, clean the entire surface using mechanical methods, such as high-pressure water jetting. The surface must be consistent and firm, with no tendency to crumble or flake off. If the substrate needs levelling, repair it using the appropriate products from the TKROMPLAST range. To even out absorption and consolidate the surface, apply one coat of TKROM FIJATIVO F-1, TKROM FIJATIVO F-4 or TKROM FIJADOR AL AGUA PLIOTEC.

### ALREADY PAINTED SURFACES:

Outdoors, clean the entire surface using mechanical methods, such as high-pressure water jetting. Ensure that the substrate is sound and stable. Check the condition of the existing paintwork, removing any cracked and/or poorly adhered areas. Repair any imperfections and proceed as indicated for new surfaces.

### SPECIAL CONSIDERATIONS FOR SURFACES IN GOOD CONDITION

#### CONCRETE

The surface must be dry and have undergone the necessary air-curing period (minimum 4 weeks). The substrate must comply with the requirements of the concrete standard UNE-EN ISO 1504-2, specifically the performance requirements for coatings.

#### MORTARS

Removal of efflorescence and alkalinity using suitable products, for example, treatment with hydrochloric acid (sulfumán) diluted with 10 parts water.

#### FIBRE-CEMENT

Eliminating alkalinity in accordance with guidelines for mortars.

#### POROUS PLASTERS:

To prevent excessive absorption during subsequent painting, apply one coat of TKROM FIJATIVO F-4.

#### FRAGILE PLASTERS:

To strengthen the outer layer by creating a resin mesh that also allows vapour to pass through, reduces absorption and facilitates subsequent painting, apply one coat of TKROM FIJATIVO F1.

#### PLASTERS AND RENDERING:

The condition of the substrate must comply with the UNE-EN 998-2 standard for mortars, and in accordance with its specifications, the adhesion value to the substrate must meet the requirements specified in the substrate manufacturer's CE marking. Under no circumstances should it be less than 0.2 N/mm<sup>2</sup>. The average value should be 0.3 N/mm<sup>2</sup>.

#### ANTIQUÉ PAINTS:

The quality of existing coatings is important. Their adhesion must not be less than 0.7 N/mm<sup>2</sup>, and the average value from sampling must be greater than 1 N/mm<sup>2</sup> (standard UNE-EN ISO 1504-2). Ensure the entire surface is thoroughly cleaned using a steam jet or high-pressure water jet. In the case of glossy paints, open the pores using mechanical means and treat the surface as if it were new.

### SPECIAL CONSIDERATIONS FOR SURFACES IN POOR CONDITION:

#### DARKENING CAUSED BY MOULD AND ALGAE:

Proceed to remove and disinfect the stains by scrubbing them vigorously with a brush using domestic bleach. Next, treat the surface with TKROM LIMPIADOR REFORZANTE and then apply one coat of TKROM IMPRIMACIÓN SELLADORA-SANEADORA.

#### SALITRE:

Scratch with a brush or machine-polish, followed by chemical treatment with hydrochloric acid (Sulfuman) diluted with 10 parts water. Then treat with TKROM FIJATIVO F-1.

#### RUST STAINS ORIGINATING FROM SLABS:

Apply two coats of TKROM SUPERLITE ANTIMANCHAS.

#### OLD PAINT COATS WITH POOR ADHESION:

If adhesion is less than 0.7 N/mm<sup>2</sup> (UNE-EN ISO 1504-2 standard), use suitable mechanical methods to remove the old paint. The substrate must be properly prepared to accept the new finish. Proceed as with new substrates.

## SUBSTRATE PREPARATION

### INCONSISTENT SURFACES:

Surfaces with defects such as flaking, cracking, efflorescence, blistering, etc., will need to be treated by completely removing the existing paint by mechanical means. Next, apply one coat of any of the following products: TKROM FIJATIVO F-1, TKROM FIJATIVO F-4 or TKROM FIJADOR AL AGUA PLIOTEC, and proceed as indicated for new surfaces.

## APPLICATION SYSTEM

System	Product	Yield	Dilution	Coats
PRIMING (Highly porous substrates, unpainted substrates with efflorescence)	TKROM FIJATIVO F4	14–18 m <sup>2</sup> /L	1:4 water	1 or 2
PRIMING (Highly porous substrates, unpainted substrates with efflorescence)	TKROM FIJADOR AL AGUA PLIOTEC	10–14 m <sup>2</sup> /L	Undiluted	1 or 2
PRIMING (Low-absorbency surfaces, aged paints)	TKROM FIXATIVE F1	14–18 m <sup>2</sup> /L	1:1 water	1 or 2
PRIMING (Substrates containing microorganisms)	TKROM LIMPIADOR REFORZANTE	n.a.	Undiluted	1 or 2
PRIMING (Substrates with microorganisms)	TKROM IMPRIMACIÓN SELLADORA-SANEADORA	14–18 m <sup>2</sup> /L	Undiluted	1 or 2
PRIMER	TKROM SUPERCARRARA RUGOSO	5–7 m <sup>2</sup> /L	50% water	1
FINISH	TKROM SUPERCARRARA RUGOSO	3–5 m <sup>2</sup> /L	< 5% water	2

## APPLICATION CONDITIONS

Substrate and Ambient Temperature	Min. +5°C / Max. +35°C
Ambient humidity	Max. 80%
Substrate Moisture	Dry substrate with a moisture content of < 5%. Cement mortars: allow to set completely (minimum 28 days). Cement-based products: allow to dry for at least 4 days before applying the coating.
Dew Point	The substrate temperature must be at least 3°C above the dew point to reduce the risk of flaking or efflorescence.

## APPLICATION RECOMMENDATIONS

Product preparation	Stir until the product is thoroughly mixed
Application method	Brush, roller and spray application. It can be applied using a brush, a short-pile roller or sprayed using airless equipment. For application using airless equipment, use the following: pressure of 150 bar, nozzle size 0.38–0.53 mm, application angle 50°–80°.
Preparation	Stir to ensure the product is thoroughly mixed. Adjust the viscosity with water. It is advisable to apply the second coat at right angles to the first coat to achieve optimum opacity.

**ADDITIONAL INFORMATION**

---

**Health and safety**

For any information regarding safety issues relating to the use, storage, transport and disposal of waste from this product, users should consult the labelling and the latest version of the Safety Data Sheet, which contains information on the product's safety, environmental impact and toxicology.

Safety Data Sheet: Please refer to the latest version.

LER CODE: 08 01 11

WASTE TYPE: HAZARDOUS

**Storage**

The product will remain stable in its original, unopened packaging at ambient temperatures not exceeding 30 °C or falling below 5 °C for 24 months from the date of manufacture. The product must be stored in a cool, dry place, in its original, tightly sealed, undamaged packaging, protected from frost and direct sunlight.

**Tariff heading**

TARIC code: 3209 10 00

**Note**

The technical information contained in this document is provided in good faith, based on laboratory tests and practical experience under normal conditions. However, the data may vary, particularly when the material is tinted or when using intense colours, in which case parameters such as density or solids by volume may be affected without compromising the product's performance. Users are advised to verify the suitability of the product for their specific application and to request the relevant colour safety data sheet from their distributor for reference.