



# IMPRIMACIÓN SUPERLITE EXTERIOR



## SALES FORMAT

15L, 4L

## DESCRIPTION

Facade primer, based on special resins in solution. Thanks to its exceptional adhesion, penetration capacity and resistance to alkaline agents, as well as its microporous structure, which allows the substrate to breathe, it is the ideal primer for subsequent painting with TKROM SUPERLITE EXTERIOR.

## SCOPE OF APPLICATION

Outdoors  
Masonry surfaces  
Cement  
Brick or plaster walls  
Concrete

## PROPERTIES

- Toilet once dry
- Excellent workability
- High penetration power
- Excellent adhesion
- No sanding is required before repainting
- Regulates absorption
- Microporous
- High breathability

## TECHNICAL DATA

Chemical composition	Speciality acrylic resins	
Colour	White	
Finish	Matte	
Density	1.60 ± 0.05 g/ml	UNE-EN ISO 2811-1
Viscosity	5.5 ± 2 mPa.s	ASTM D 2196-10
Volume solids	48 ± 2%	UNE - EN ISO 23811
VOC	< 500 g/L. Maximum value permitted by the EU: 500 g/L	2004/42/II Category (i)
Theoretical coverage	6–8 m <sup>2</sup> /L (70 dry microns)	
Drying times	Touch-dry: 15–20 mins / Fully dry: 3 hours	
Recoating time	6 h	
Dilution	0–10% depending on the application method	
Diluents	TKROM SOL. CHLORO-RUBBER 350 / TKROM SOL. SYNTHETICS 345	
Cleaning	TKROM DISOLVENTE UNIVERSAL 302	

The technical data specified may vary if the material is tinted.

## PREPARATION OF THE SUBSTRATE

### GENERAL INFORMATION

Outdoors, do not apply if rain is forecast, in the midday sun or on damp days.

### CEMENT, CONCRETE AND MASONRY SURFACES IN GENERAL

Check the condition of the wall surface and repair any imperfections using suitable mortars or products. Remove any remaining lime or distemper paint. Apply one or two coats of TKROM IMPRIMACION SUPERLITE.

## APPLICATION CONDITIONS

Substrate temperature	Min. + 5°C / Max. + 35°C
Ambient temperature	5°C / 35°C
Dew Point	The substrate temperature must be at least 3°C above the dew point to reduce the risk of peeling or efflorescence.

## APPLICATION SYSTEM

System	Product	Yield	Dilution	Coats
<b>PRIMING (Cement, Concrete and Masonry in general)</b>	TKROM SUPERLITE EXTERIOR PRIMER	6–8 m <sup>2</sup> /L per coat	0–10% ACCORDING TO THE TKROM DTE CHLOROCAUCHO 350 / TKROM DTE SYNTHETICS 345 SYSTEM	1 or 2
<b>FINISH</b>	TKROM SUPERLITE EXTERIOR	8–10 m <sup>2</sup> /L per coat	5–15% ACCORDING TO THE TKROM DTE CHLORO-RUBBER 350/TKROM DTE SYNTHETICS 345 SYSTEM	1 or 2

## APPLICATION RECOMMENDATIONS

<b>Product preparation:</b>	Shake until the product is thoroughly homogenised. Shake again periodically. Adjust the viscosity. During lengthy processes, evaporation will occur; readjust the viscosity. If the solvent is excessively potent, it may be advisable to reduce its proportion.
<b>Application method:</b>	Can be applied by brush, roller or airless spray gun. For application by brush, roller or airless spray gun, dilute the product with a small amount (0–10%) of TKROM CHLORO-RUBBER SOLVENT and SUPERLITE EXTERIOR 350.

## ADDITIONAL INFORMATION

<b>Health and safety</b>	For any information regarding safety issues relating to the use, storage, transport and disposal of waste from this product, users should consult the labelling and the latest version of the Safety Data Sheet, which contains physical, ecological and toxicological data, as well as other relevant information on this subject. WASTE: HAZARDOUS. LER CODE: 080111
<b>Storage</b>	The product will remain stable in its original, unopened packaging at ambient temperatures not exceeding 30°C or falling below 5°C for 24 months from the date of manufacture. The product must be stored in a cool, dry place, in its original packaging, tightly sealed, undamaged and protected from frost and direct sunlight.
<b>Tariff heading</b>	TARIC code: 3208 20 90
<b>Note</b>	The technical information contained in this document is provided in good faith, based on laboratory tests and practical experience under normal conditions. However, the data may vary, particularly when the material is tinted or when using intense colours, in which case parameters such as density or solids by volume may be affected without compromising the product's performance. Users are advised to verify the suitability of the product for their specific application and to request the relevant colour safety data sheet from their distributor for reference.