

TKROM IMPRIMACION SUPERLITE



PRODUCT DESCRIPTION

Primer for façades, based on special diluted resins. Due to its exceptional adhesion, penetrating power and resistance to alkaline agents, this product is ideal as a first coat to be painted over with TKROM SUPERLITE EXTERIOR.

USES / SCOPE OF APPLICATION

- For all kinds of construction surfaces.
- For indoor or outdoor use.
- Cement.
- Brick or gypsum walls.
- Concrete.

CONTAINER	SIZE
Metal	4 L
Metal	15 L

CHARACTERISTICS / BENEFITS

- Odourless when dry.
- Excellent ease of application.
- Good penetrative power.
- Adhesive.
- There is no need of sanding for painting over.
- Regulates absorption.
- Micro-porous. High breathability.

PRODUCT PROPERTIES

APPEARANCE OF THE DRY FILM	VALUE	STANDARD	REPORT
COLOUR	Blanco		
FINISH	Mate		
CHROMATIC COORDINATES, L*	90 a 92	UNE 48073	IL-6609-02
CHROMATIC COORDINATES, a*	-0,60 a -0,40	UNE 48073	IL-6609-02
CHROMATIC COORDINATES, b*	2,80 a 3,00	UNE 48073	IL-6609-02
BERGER WHITENESS	66-68	UNE 48073	IL-6609-02
OPACITY	87-89%	UNE-EN ISO 6504-3	IL-6609-05

PHYSICAL PROPERTIES	VALUE	STANDARD	REPORT
DENSITY	1,57-1,61 g/ml	UNE-EN ISO 2811-1	

REFERRING TO ITS FORMULATION	VALUE	STANDARD	REPORT
CONTENT IN NON-VOLATILE MATERIAL (MASS)	71-73%	UNE-EN ISO 3251	
CONTENT IN NON-VOLATILE MATERIAL (VOLUME)	47-49%	UNE-EN ISO 23811	
MAXIMUM ADMISSIBLE COV CONTENT	500 g/L	2004/42/II A clasificación	
MAXIMUM ADMISSIBLE COV CONTENT IN THE PRODUCT	500 g/L	2004/42/II A clasificación	

tkrom®

APPLICATION PROPERTIES	VALUE	STANDARD	REPORT
THEORETICAL YIELD	5-7 m ² /L - 3-5 m ² /kg a 75µm secas	UNE-EN ISO 23811	
THINNING	0-10%	SEGÚN SISTEMA APLICACIÓN	
THINNER	TKROM Disolvente 350 Clorocaucho y Superlite Exterior / TKROM Disolvente 345 Sinteticos y Grasos		

MEDIUM CONDITIONS

MEDIUM PREPARATION

CEMENT, CONCRETE AND OTHER CONSTRUCTION SURFACES

- Check the condition of the wall surface and use mortar or appropriate products to repair any imperfections. Remove any remains of lime or tempera paint that may be present. Apply one or two coats of TKROM SUPERLITE PRIMER.

APPLICATION SYSTEM

SYSTEM	PRODUCT	THEORETICAL YIELD	DILUTION	COATS
PRIMING (CEMENT, CONCRETE AND MASONRY IN GENERAL)	TKROM SUPERLITE PRIMER	5-7 m ² /l per coat	0%-10% CHLORINATED RUBBER THINNER AND SUPERLITE EXTERIOR TDS- 6934 or 345 SYNTHETIC THINNER TDS- 6914	1 or 2

APPLICATION PROCESSES

PROCESS	INSTRUCTIONS
PRODUCT PREPARATION	<ul style="list-style-type: none"> · Stir until the mixture is properly homogenised. · Stir again at regular intervals. · Adjust viscosity. · Evaporation will take place during prolonged application, so the viscosity will have to be adjusted. · If the thinning agent is very strong, the proportion may have to be reduced.
APPLICATION	<ul style="list-style-type: none"> · It can be applied with a brush, roller or airless paint sprayer. · To apply with a brush, roller or airless paint sprayer, dilute the product with a small amount (0%-10%) of Tkrom Chlorinated Rubber Thinner and Superlite Exterior Thinner TDS-6934.
TOOL CLEANING	<ul style="list-style-type: none"> · All tools that are used must be cleaned immediately after use with any of the recommended thinners, or with TKROM 302 UNIVERSAL THINNER (TDS-6961).

WAIT TIMES

Drying at 20°C and 65% relative humidity: The product is touch dry in 15-20 minutes. Dry for painting over in 6 hours.



SAFETY

Users should refer to the labelling and the latest version of the product's Safety Data Sheet for any information regarding safety issues related to use, storage, transport and waste disposal. The Safety Data Sheet contains all of the physical, environmental and toxicological data on the product, and information on all other issues related to this topic.

SAFETY SHEET	LER CODE	WASTE TYPE
MSDS-6609	08 01 11	HAZARDOUS

STORAGE

When kept in its original unopened container at room temperatures below 30°C and above 5°C, the product will remain stable for 24 months from the date of manufacture.

It should be stored in a cool, dry place, in its original properly sealed and undamaged container, protected from frost and direct sunlight.

TARIFF HEADING

TARIC code: 3208 20 90

Note: The data presented in this technical data sheet may be modified based on possible changes in formation. In any case, values are provided for information purposes only, and the suitability of the product for a certain job should always be tested.

