

# ACRYPLAS SMOOTH PROFESSIONAL COATING

FORMAT: 15L / 4L

Smooth coating for facades, based on acrylic copolymer dispersion. Specially formulated for professional use in both new construction and renovation.

- ✓ Waterproof
- ✓ Breathable
- ✓ Resistance to atmospheric agents
- ✓ High adhesion
- ✓ Suitable for new construction and renovation



FINISH	MATE	UNE-EN 13300
COLOUR	WHITE	
DENSITY	1,64± 0,05 Kg/L	ISO 2811-1
PH	8,5 - 9,2	
OPACITY	93± 2 % (for a yield of 8 m <sup>2</sup> /L at 120 wet microns)	ISO 6504-3
THEORETICAL PERFORMANCE	7-9 m <sup>2</sup> /L (60 microns dry)	ISO 23811
BERGER WHITENESS	92± 2	UNE 48073
VISCOSITY	22± 3 Pa-s (20rpm, R6)	ASTM D 2196-10
SOLIDS IN VOLUME	47± 2	ISO 23811
MAX. CONTENT COV PERMITTED/PRODUCT	40 g/l / <20 g/l	2004/42/IIA

TOUCH-DRYING	15 - 20 MIN
REPOINTING	4 HOURS
TOTAL DRYING	10 - 15 DAYS
TARIC CODE	3209 10 00
SAFETY DATA SHEET	MSDS - 0220
TYPE OF WASTE	NON DANGEROUS

**1)** Ensure that the substrate is compact and firm. **2)** Stir until the product is well homogenised. **3)** Respect the dilution quantities and drying times between coats. **4)** Clean the tools with water immediately after use. **5)** It is not recommended to wash the walls until 24 days after application.

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
PRIMING	ACRYPLAS FIXATIVE TOTAL PRO	14-18 m <sup>2</sup> /l	1:3	1
PRIMING	ACRYPLAS SMOOTH	8-10 m <sup>2</sup> /l	10-20 % WATER	1
FINISH	ACRYPLAS SMOOTH	7-9 m <sup>2</sup> /l	<10 % WATER	2

The data indicated in this technical data sheet may be modified according to possible variations in formulation and, in any case, express indicative values which do not exempt from carrying out the appropriate tests on the suitability of the product for a specific job.