

ACRYPLAS MATT Q1

PROFESSIONAL PAINTING

FORMAT: 15L / 4L

Matt wall paint based on an emulsion of a styrenated acrylic copolymer. **Especially for decoration of interior walls and ceilings.** When dry, it leaves a soft and smooth film with a pleasant silky sheen.

- ✓ Indoor
- ✓ Masonry surfaces.
- ✓ Matt finish
- ✓ Excellent coverage
- ✓ Good adhesion
- ✓ Good performance
- ✓ High transpiration
- ✓ Good whiteness



FINISH	SEMI MATTE	UNE-EN 13300
COLOUR	WHITE	
DENSITY	1,72± 0,05 Kg/L	ISO 2811-1
PH	8,5 - 9,2	
OPACITY	98± 2% (for a yield of 8 m ² /L at 120 wet microns)	ISO 6504-3
THEORETICAL PERFORMANCE	8-10 m ² /L (60 microns dry)	ISO 23811
BERGER WHITENESS	110± 2	UNE 48073
VISCOSITY	15± 5 Pa-s (20rpm, R6)	ASTM D 2196-ASTM D 2196-10
SOLIDS IN VOLUME	47 ± 2 %	ISO 23811
MAX. COV CONTENT ALLOWED/PRODUCT	30 g/l / <20 g/l	2004/42/IIA
TOUCH-DRYING	15 - 20 MIN	
REPINTING	4 HOURS	
TOTAL DRYING	10 - 15 DAYS	
TARIC CODE	3209 10 00	
SAFETY DATA SHEET	MSDS - 0102	
TYPE OF WASTE	NON DANGEROUS	

1) Make sure that the substrate is compact and firm. **2)** Shake until the product is well homogenised. **3)** Respect the dilution quantities indicated in the table **4)** Clean the tools with water immediately after use. **5)** It is not recommended to wash the walls until 24 days after application.

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
PRIMING	FIXED TOTAL PRO	14-18 m ² /l	1:3	1
PRIMING	ACRYPLAS MATT Q1	9-11 m ² /l	10-15% WATER	1
FINISH	ACRYPLAS MATT Q1	8-10 m ² /l	5-10% WATER	2

The data indicated in this technical data sheet may be modified according to possible variations in formulation and, in any case, express indicative values which do not exempt from carrying out the appropriate tests on the suitability of the product for a specific job.