

ACRYPLAS STONE PROFESSIONAL COATING

FORMAT: 15L / 4L

Stone-based coating for façades, breathable, with good hardness and adherence to the different materials used in construction, and resistant to atmospheric agents.

- ✓ Waterproof
- ✓ Breathable
- ✓ Resistance to atmospheric agents
- ✓ High adhesion
- ✓ Suitable for new construction and renovation



FINISH	MATE	UNE-EN 13300
COLOUR	WHITE	
DENSITY	1,54± 0,05 Kg/L	ISO 2811-1
PH	8,5 - 9,2	
OPACITY	94± 2 % (for a yield of 8 m²/L at 100 wet microns)	ISO 6504-3
THEORETICAL PERFORMANCE	7-9 m²/L (60 microns dry)	ISO 23811
BERGER WHITENESS	106± 2	UNE 48073
VISCOSITY	15± 3 Pa-s (20rpm, R6)	ASTM D 2196-10
SOLIDS IN VOLUME	42± 2	ISO 23811
MAX. CONTENT COV PERMITTED/PRODUCT	40 g/l / <25 g/l	2004/42/IIA

TOUCH-DRYING	15 - 20 MIN
REPOINTING	4 HOURS
TOTAL DRYING	10 - 15 DAYS
TARIC CODE	3209 10 00
SAFETY DATA SHEET	MSDS - 0221
TYPE OF WASTE	NON DANGEROUS

1) Make sure that the substrate is compact and firm. **2)** Stir until the product is well homogenised. **3)** Respect the dilution quantities and drying times between coats. **4)** Clean the tools with water immediately after use. **5)** It is not recommended to wash the walls until 24 days after application.

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
PRIMING	ACRYPLAS FIXATIVE TOTAL PRO	14-18 m²/l	1:3	1
PRIMING	ACRYPLAS STONE	7-9 m²/l	10-20 % WATER	1
FINISH	ACRYPLAS STONE	6-8 m²/l	<5 % WATER	2

The data indicated in this technical data sheet may be modified according to possible variations in formulation and, in any case, express indicative values which do not exempt from carrying out the appropriate tests on the suitability of the product for a specific job.