ACRYPLAS SATIN Q1 PROFESSIONAL PAINTING

FORMAT: 15L) / 4L

Satin plastic paint based on vinyl copolymers in emulsion. Excellent value for money, very good whiteness and washability, excellent adhesion and good hiding power.

- $\sqrt{}$ Masonry surfaces.
- √ Satin finish
- $\sqrt{Non-yellowing}$
- $\sqrt{}$ Good adhesion
- √ High wet scrub
- $\sqrt{}$ Very good whiteness



FINISH / COLOUR	SATIN / WHITE UNE-EN 13300		
DENSITY	1,22± 0,05 Kg/L	ISO 2811-1	
РН	8,5 - 9,2		
ΟΡΑCITY	93± 2 % (for an efficiency of 8 m²/L at 120 wet microns)	ISO 6504-3	
THEORETICAL PERFORMANCE	4-6 m ² /L (50 microns dry)	ISO 23811	
60º / 85º BRIGHTNESS	22 ±5 UB/ 51 ±5 UB	UNE 48073	
VISCOSITY	11± 3 Pa-s (20rpm, R6)	ASTM D 2196-10	
BERGER WHITENESS	100± 2	UNE 48073	
SOLIDS IN VOLUME	25± 2	ISO 23811	
MAX. CONTENT COV PERMITTED/PRODUCT	100 g/l / <1g/l	2004/42/IIA	
TOUCH-DRYING	30-35 MIN		
REPINTING	4 HOURS		
TOTAL DRYING	10 - 15 DAYS		
TARIC CODE	3209 10 00		
SAFETY DATA SHEET	MSDS - 0161		
TYPE OF WASTE	NON DANGEROUS		

1) Ensure that the substrate is compact and firm. 2) Shake until the product is well homogenised. 3) Respect the dilution quantities indicated in the table 4) Clean the tools with water immediately after use. 5) It is not recommended to wash the walls until 24 days after application.

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
PRIMING	FIXED TOTAL PRO	14-18 m²/l	1:3	1
PRIMING	ACRYPLAS SATIN Q1	5-7 m²/l	10-15% WATER	1
FINISH	ACRYPLAS SATIN Q1	4-6 m²/l	5-10% WATER	2

The data indicated in this technical data sheet may be modified according to possible variations in formulation and, in any case, express indicative values which do not exempt from carrying out the appropriate tests on the suitability of the product for a specific job.

tkrom.com



