

ACRYPLAS SATIN Q2

PROFESSIONAL PAINTING

FORMAT: 15L / 4L

Satin plastic paint with low VOC levels, based on copolymers in dispersion. Excellent balance between application, coverage, whiteness, performance and washability. Suitable for professional use.

- ✓ Interiors
- ✓ Masonry surfaces.
- ✓ Smooth satin finish
- ✓ Excellent coverage
- ✓ Good washability
- ✓ High performance
- ✓ Low levels of VOCs



FINISH / COLOUR	SATIN / WHITE	UNE-EN 13300
DENSITY	1,22± 0,05 Kg/L	ISO 2811-1
PH	8,5 - 9,2	
OPACITY	90 ± 2 % (for an efficiency 8 m ² /L at 120 µm wet)	ISO 6504-3
THEORETICAL PERFORMANCE	4-6 m ² /L (50 microns dry)	ISO 23811
60º / 85º BRIGHTNESS	18 ±5 UB/ 43 ±5 UB	UNE 48073
VISCOSITY	5± 3 Pa-s (20rpm, R4)	ASTM D 2196-10
BERGER WHITENESS	100± 2	UNE 48073
SOLIDS IN VOLUME	27± 2	ISO 23811
MAX. CONTENT COV PERMITTED/PRODUCT	100 g/l / <1g/l	2004/42/IIA

TOUCH-DRYING	30-35 MIN
REPINTING	4 HOURS
TOTAL DRYING	10 - 15 DAYS
TARIC CODE	3209 10 00
SAFETY DATA SHEET	MSDS - 0171
TYPE OF WASTE	NON DANGEROUS

1) Make sure the support is compact and firm. **2)** Shake until the product is well homogenised. **3)** Respect the dilution quantities indicated in the table **4)** Clean the tools with water immediately after use. **5)** It is not recommended to wash the walls until 24 days after application.

SYSTEM	PRODUCT	PERFORMANCE	DILUTION	LAYERS
PRIMING	FIXED TOTAL PRO	14-18 m ² /l	1:3	1
PRIMING	ACRYPLAS SATIN Q2	5-7 m ² /l	10-15% WATER	1
FINISH	ACRYPLAS SATIN Q2	4-6 m ² /l	5-10% WATER	2

The data indicated in this technical data sheet may be modified according to possible variations in formulation and, in any case, express indicative values which do not exempt from carrying out the appropriate tests on the suitability of the product for a specific job.